

CYCOM® 950

Епоxy; Epoxide

Cytec Industries Inc.

Описание материалов:

CYCOM® 950 resin is a 250 - 300°F (121 - 149°C) curing epoxy resin with good 220°F (104°C) dry service capability. It can be impregnated via hot melt or solution techniques on all available fibers and fabrics. CYCOM 950 is formulated for shrink tape processing, but it has been successfully processed by autoclave, press molding and vacuum bagging. Unidirectional tape and woven fabric impregnated with CYCOM 950 resin will retain excellent tack and drape for at least 10 days at 72°F (22°C). Standard cure is for 90 minutes at 275°F (135°C). No post cure is required for 220°F (104°C) dry service capability.

The recommended autoclave lay-up procedure for this material is L-3 or L-6. The recommended cure procedure is C-6 or C-7 at 275°F (135°C).

Suggested Applications: Tubular structures such as fishing rods, golf shafts and bike components

Главная Информация	
Характеристики	Автоклавный Термическое лечение Низкий поток
Используется	Ламинаты Спортивные товары Трубка
Формы	Ткань Волокно
Метод обработки	Пресс-форма Вакуумная формовка

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

