

## Harpweld™ 1384

Thermoplastic

Hapco Inc.

### Описание материалов:

A 100% solids room temperature curing polymer adhesive system ideally suited to be used as a bond between similar and dissimilar substrates. May be used as an all-purpose, room-curing, polymer adhesive, particularly because of its excellent handling properties. It also provides the ideal mix ratio of 1:1 (by volume), making HAPWELD 1384 convenient to use for both hand and machine mixing. The A & B composites are black and white, turning grey when mixed.

Главная Информация		
Характеристики	Bondability	
	Высокая прочность	
Используется	Клеи	
Внешний вид	Серый	
Формы	Жидкость	
Физический	Номинальное значение	Единица измерения
Weight		
Per gallon - Part A	5400	g
Per gallon - Part B	5000	g
Cure Time	1.0 to 2.0	day
Время работы (23 °C)	12.0 to 16.0	hr
Механические	Номинальное значение	Единица измерения
Прочность сдвига	17.2 to 20.7	MPa
Термокомплект	Номинальное значение	Единица измерения
Срок службы горшка (25°C)	30	min
Терморегулирующая вязкость <sup>1</sup> (24°C)	25500	cP
NOTE		
1.	Range: 25000 to 30000	

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

