

Polymist® XPP 515

Polytetrafluoroethylene

Solvay Specialty Polymers

Описание материалов:

Polymist® 515 a white PTFE micronized powder PTFE micronized powder composed of discrete particles.

Designed for use in critical engineering and high end performance plastics applications, Polymist® XPP 515 will improve wear resistance and low coefficient of friction.

Polymist® XPP 515 can also be used in elastomers to improve abrasion and tear resistance as well as non-stick properties, mar and abrasion resistance.

Main features of Polymist® 515 are:

Improved wear resistance

Increased pressure x velocity (PV) limits

Reduced friction and stick-slip response

Improved lubricity, abrasion, scratch and rub resistance

Increased (hot) tear strength

Главная Информация	
--------------------	--

Используется	Добавка
Внешний вид	Белый
Формы	Порошок

Физический	Номинальное значение	Единица измерения	Метод испытания
Удельная площадь поверхности	3.0	m ² /g	Internal method
Размер частиц-(D50)	20.0	µm	Internal method
Плотность объема	400	g/l	ASTM D4895
Температура расплава	320 - 330	°C	ASTM D3418

Дополнительная информация	Номинальное значение	Единица измерения	Метод испытания
---------------------------	----------------------	-------------------	-----------------

Processing Polymist® XPP 515 can be used in a wide variety of different thermoplastics. Typical loadings are 5 - 20% by weight of the compound and the optimum loading is dependent by the resin type and the desired final properties of the part. Besides its main function as a friction and wear additive, Polymist® XPP 515 can be also used at lower concentration to provide the following properties:

Processing aid to improve compounding and molding conditions

Mold release agent due to non-stick properties

Polymist® XPP 515 can be incorporated into thermoplastics by pre-mixing or co-feeding with the base polymer using standard industrial equipment and technology. The compound can also be prepared by first using a masterbatch.

Storage and Handling

The usual precautions for safe storage and handling of Polymist® XPP 515 should be taken according to material safety documentation and experience. There will be no chemical deterioration of the Polymist® XPP 515 during proper storage.

Shelf life of Polymist® XPP 515 micronized powders will vary depending upon whether the recommended storage conditions are maintained and whether the material remains free from foreign contamination during storage time (not exposed to dirt, dust, water or other chemicals). The material should remain sealed in the original containers and storage conditions should provide for protection from temperature extremes as well as rain, snow or other wet environments (or such conditions which may damage the storage containers in which the product is stored).

Safety and Toxicology

Before using PTFE Polymist® XPP 515 micronized powders consult the product Material Safety Data Sheet and follow all label directions and handling precautions.

As with all PTFE materials, handling and processing should only be carried out in well ventilated areas. Vapor extractor units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Do not smoke in areas contaminated with powder, vapor or fumes. See Material Safety Data Sheet for detailed advice on waste disposal methods.

Packaging

Polymist® XPP 515 is packaged in 25 kg non returnable drums. Each drum has one bag liner made of polyethylene resin.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

