

## KYOCERA IMIDALLOY KIR-30

Thermoset Polyimide

KYOCERA Chemical Corporation

### Описание материалов:

"IMIDALLOY" KIR-30 is best suitable binder for Diamond grind wheel , Friction materials, etc.

Strong Points

Excellent Heat resistance

Excellent Adhesion property

Excellent Moldability

Environmental friendly

"IMIDALLOY" have Excellent Heat resistance and Excellent Adhesion property to organic material. We have a lot of sales performance in the grind wheel purpose.

Главная Информация		
Характеристики	Экологически чистый	
	Хорошая адгезия	
	Хорошая плавность	
	Высокая термостойкость	
Используется	Электрическое/электронное применение	
Физический	Номинальное значение	Единица измерения
Удельный вес	1.30 to 1.40	g/cm <sup>3</sup>
Видимая плотность	0.30 to 0.45	g/cm <sup>3</sup>
Decomposition Temperature	340 to 350	°C
Softening Point	105 to 125	°C
Median Particle Size	20.0 to 30.0	µm
Uncured Properties	Номинальное значение	Единица измерения
Gel Time (200°C)	1.0 to 2.0	min

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

### Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat