

Algoflon® L203

Polytetrafluoroethylene

Solvay Specialty Polymers

Описание материалов:

Algoflon® L203 a white PTFE micronized powder produced from dispersion polymerization comprising loose agglomerates of sub-micon sized primary particles.

Algoflon® L203 can be de-agglomerated to sub-micron particle size by the application of shear providing a better dispersion and distribution of the PTFE particles in the application.

Designed for use in critical engineering and high end performance lubricants to improve thickening effect, lubricity, Algoflon® L203 improves also corrosion and temperature resistance.

Main features of Algoflon® L203 include:

High specific surface area

Low molecular weight

Good blendability

Deagglomerated under shear

Главная Информация			
Используется	Добавка		
Внешний вид	Белый		
Формы	Порошок		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельная площадь поверхности	> 7.5	m ² /g	Internal method
Средний размер частиц-Поверхность	5.0	µm	Internal method
Плотность объема	325	g/l	ASTM D3418
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Пиковая температура плавления	325 - 335	°C	ASTM D3418
Дополнительная информация			

Processing Algoflon® L203 is an ideal additive for lubricants with respect to any other solid additive because they offer:

- Low coefficient of friction and reduced wear
- Outstanding chemical and corrosion resistance
- High temperature resistance
- Good low temperature torque

Algoflon® L203 micronized powder is ideal for dispersing in oils, greases and pastes to improve both high and low temperature lubricity and is preferred over conventional additives, such as graphite or molybdenum disulfide whenever potential staining cannot be tolerated. Greases incorporating up to 30% by weight of Algoflon® L203 micronized powder are effective for much longer periods than conventional greases so that lubrication frequency may be reduced substantially. Extreme environmental demands on greases, such as those experienced in the automotive industry (i.e. wide temperature ranges and heavy loads) can be accommodated by the addition of Algoflon® L micronized powders.

Storage and Handling

The usual precautions for safe storage and handling of Algoflon® L203 should be taken according to material safety documentation and experience. There will be no chemical deterioration of the Algoflon® L203 during proper storage.

Shelf life of Algoflon® L203 micronized powders will vary depending upon whether the recommended storage conditions are maintained and whether the material remains free from foreign contamination during storage time (not exposed to dirt, dust, water or other chemicals). The material should remain sealed in the original containers and storage conditions should provide for protection from temperature extremes as well as rain, snow or other wet environments (or such conditions which may damage the storage containers in which the product is stored).

Safety and Toxicology

Before using PTFE Algoflon® L micronized powders consult the product Material Safety Data Sheet and follow all label directions and handling precautions.

As with all PTFE materials, handling and processing should only be carried out in well ventilated areas. Vapor extractor units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Do not smoke in areas contaminated with powder, vapor or fumes. See Material Safety Data Sheet for detailed advice on waste disposal methods.

Packaging

Algoflon® L203 is packaged in 20 kg non returnable drums. Each drum has one bag liner made of polyethylene resin.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

СВЯЖИТЕСЬ С НАМИ

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

