

CPI PP 40 Natural

40% стекловолокно

Polypropylene

CPI Binani, Inc.

Описание материалов:

The materials engineers at CPI Binani formulate materials to match the performance requirements called out in your program.

By combining specific quantities of polypropylene, fiber glass, UV protection, and or fire retardant, along with additives designed to make the recipe perform optimally, we create a recipe ideally suited to your needs.

Polypropylene is a cost effective, material that when enhanced in the D-LFT process can deliver value. The following table is an example of one formulation.

Главная Информация		
Наполнитель/армирование	Стекловолокно, 40% наполнитель по весу	
Внешний вид	Натуральный цвет	
Механические	Номинальное значение	Единица измерения
Модуль растяжения	8280	МПа
Прочность на растяжение	123	МПа
Флекторный модуль	6760	МПа
Flexural Strength	191	МПа
Poisson's Ratio	0.35	
Воздействие	Номинальное значение	Единица измерения
Зубчатый изод Impact	390	J/m

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat