

## Honghai CM 352L

Chlorinated Polyethylene

Weifang Honghai Plastics Technology Co., Ltd.

### Описание материалов:

This product is a kind of saturated thermoplastic elastomer with irregular structure, almost no crystal. It features lower plasticizing temperature and Mooney viscosity, excellent processing flowability, good heat resistance, weatherability, flex durability and flame retardancy. It not only can be used as halogen rubber alone but also can be used with CR, CSM, NBR, SBR, NR and so on together by mixing in random proportion.

This product not only can be used for special synthetic rubber but also can be used for modifier of general-purposed synthetic rubber and plasticizer of PVC etc. It can be used for making all kinds of wires, cable sheath, rubber hose, flame retarding conveyor belt, rubber wares, seal strip of adhesive board, insulation of wires and cables and waterproof membrane for roof etc.

Главная Информация	
Характеристики	Хорошая мобильность Хорошая гибкость Хорошая устойчивость к погоде Теплостойкость, средняя Долговечность Огнестойкий
Используется	Конвейер Применение проводов и кабелей Труба Пластиковая модификация

Физический	Номинальное значение	Единица измерения	Метод испытания
Вязкость Mooney (ML 1+4, 125°C)	45 - 55	MU	GB/T 1232
Содержание хлора	34.0 - 36.0	wt%	GB/T 7139
Decomposition Temperature	> 165	°C	HG/T 2704
Остатки сита-20 меш		%	GB/T 2916
Тепло плавления		J/g	DSC
Испарители		%	GB/T 2914

Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра (Shore A)	< 56		GB/T 2411

Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение	> 6.00	MPa	GB/T 528
Удлинение при растяжении (Break)	> 700	%	GB/T 528

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

