

SEALUTION™ 230 Peel Polymer

Peel Polymer

The Dow Chemical Company

Описание материалов:

SEALUTION™ 230 Peel Polymer is a high clarity peelable sealant that gives a peelable seal to itself, polypropylene and polyethylene. It is suitable for use in cast film lines.

Main Characteristics:

Pellet form

Peelable sealant to itself, PP and PE

Good optics

Complies with:

EU, No 10/2011

U.S. FDA

Consult the regulations for complete details.

Главная Информация			
Рейтинг агентства	FDA не рассчитан		
	Европа без 10/2011		
Формы	Частицы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	0.897	g/cm ³	ASTM D792
Массовый расход расплава (MFR) (190°C/2.16 kg)	3.3	g/10 min	ASTM D1238
Пленки	Номинальное значение	Единица измерения	Метод испытания
Толщина пленки протестирована	51	µm	
Температура инициализации уплотнения ¹ (51 µm, Blown Film)	95.0	°C	Internal method
Привлекательный диапазон ²	95 - 180	°C	Internal method
Оптический	Номинальное значение	Единица измерения	Метод испытания
Haze ³ (50.0 µm, Blown Film)	< 10	%	ISO 14782
Экструзия	Номинальное значение	Единица измерения	
Температура расплава	190 - 230	°C	
Инструкции по экструзии			
Fabrication Conditions For Cast Film:			
Die Gap: 1.5 mm			
Melt Temperature: 190-230°C			
Coextruded cast film:			
Total film thickness: 50 microns			
A / B Coex, 80% / 20% layer ratio			
A = LLDPE/LDPE blend or random PP (40 µm)			
B = SEALUTION 230 (10 µm)			
NOTE			

1. Temperatures at which 2 N/15 mm heat seal strength is achieved. Heat Seal Strengths, Topwave HT Tester 0.5 s dwell, 500 N pressure, pull speed 100 mm/min.
2. Peelable range of 3-5 N/15 mm. for this particular structure, seal to itself. Heat Seal Strengths, Topwave HT Tester 0.5 s dwell time, 500 N pressure, pull speed 100 mm/min.
3. Haze for this particular structure

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

