

Sumiliteresin® PR-1019 I

Phenolic

SBHPP

Описание материалов:

SUMILITERESIN® PR-1019 I is Hexa Adducted Phenolic Resin (HAP) Straight novolac type powder form phenolic resin.

Characteristics

SUMILITERESIN® PR-1019 I has high molecule number, hexamine content about 13% and pre-reacted hexamine to novolac (HAP-resin).

For Friction Material : High hardness, good moldability, good wearability, heat stability and good friction coefficient.

For Bonded Abrasive : oven process can be decreased, High heat resistance and preferable apply for snagging wheel.

Главная Информация		
Характеристики	Хорошая производительность формования Хорошая стойкость к истиранию Теплостойкость, высокая Термическая стабильность, хорошая Высокая твердость	
Внешний вид	Белый Желтый	
Формы	Порошок	
Физический	Номинальное значение	Единица измерения
Длина потока (125°C)	0.80 - 1.80	cm
Анализ сита-150µm		%
Тепловой	Номинальное значение	Единица измерения
Температура плавления	97.0 - 107	°C
Uncured Properties	Номинальное значение	Единица измерения
Gel Time (150°C)	1.3 - 1.8	min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

