

Clear Cote™ Crystal Clear Table Top Epoxy

Epoxy; Epoxide

Club Kit, Inc.

Описание материалов:

CLEAR COTE™ UV Stable Crystal Clear, Table Top Epoxy System is a high performance two component clear epoxy system designed for table tops, bars, wood finishes, see-through encapsulations, art work, and other applications requiring a clear, strong, plastic coating specifically designed to resist yellowing caused by the sun and other Ultra Violet light sources. The material has an easy to use 1 to 1 by volume mix ratio, wets out substrates well, maintains its integrity over sharp corners, it has excellent air release qualities, and a relatively fast set time for an epoxy coating which may be accelerated by mild heat to 160F. While this material will do much better than competitors products for non yellowing we still do not recommend it for permanent outdoor applications.

Advantages:

100% Solids

Self Leveling, High Gloss

U.V. Resistant Formula

Excellent Air Release

Excellent Color Stability

Improved Impact Strength

Improved Surface Appearance

Early Development of Physical and Performance Properties

Produces a Tough, High Gloss, Water Resistant Coating

Eliminates Craters, Crawling and Fish Eyes

Blush Resistant

Главная Информация

Характеристики	Румяна устойчивы Хорошая стабильность цвета Хорошая прочность Хорошая устойчивость к ультрафиолетовому излучению Высокая четкость Глянцевый Низкое поглощение воды	
Используется	Клеи Нанесение покрытия Столешница Flatstocks Мебель Настольные товары	
Внешний вид	Прозрачный/прозрачный	
Термокомплект	Номинальное значение	Единица измерения
Компоненты термокомплекта		

Mix Ratio by Volume: 1.0

Part A

Mix Ratio by Weight: 100

Mix Ratio by Volume: 1.0

Part B

Mix Ratio by Weight: 83

Uncured Properties	Номинальное значение	Единица измерения
Цвет		
-- 1	Clear/Transparent	
-- 2	Clear/Transparent	
Время отверждения	24 to 48	hr
Gel Time	20 to 30	min
Tack Free Time	120 to 180	min
Cured Properties	Номинальное значение	Единица измерения
Твердость по суху (Shore D)	70	
Удлинение при разрыве	> 15	%
NOTE		
1.	Part B	
2.	Part A	

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

СВЯЖИТЕСЬ С НАМИ

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

