

## Dow ENDURANCE™ HFDA-0801 BK

Supersmooth, Extra-Clean, Crosslinkable Semiconductive Shielding Compound

The Dow Chemical Company

### Описание материалов:

DOW ENDURANCE™ HFDA-0801 BK is a specially formulated semiconductive, vulcanizable compound designed for conductor shield and bonded insulation shield applications in medium and high voltage crosslinked polyethylene insulated cables.(1) DOW ENDURANCE™ HFDA-0801 BK has demonstrated compatibility with copper and aluminum conductors.

DOW ENDURANCE™ HFDA-0801 BK was specifically developed utilizing a special acetylene carbon black to provide a supersmooth surface to achieve best in class performance and yielding a more perfect interface between the extruded shield and the insulation. As a result, significantly improved cable performance can be expected.

#### Specifications

DOW ENDURANCE™ HFDA-0801 BK is designed for use in power distribution cables. Cables with conductor and insulation shielding of DOW ENDURANCE™ HFDA-0801 BK, prepared using sound commercial fabrication practice, would be expected to meet the following specifications:

AEIC: CS8, CS9

IEC: 60502, 60840, 62067

ICEA: S-108-720; S-94-649; S-97-682, S-93-639

DIN: VDE 0276-632, 0276-620

BS: 6622

CENELEC: HD620 S1, HD632 S1

ISO 1872-E/BA, KHXY, 23-G200, C40

NF: C33-223, C33-226

UTE: C 33-223

(1) DOW ENDURANCE™ HFDA-0801 BK is recommended for use in conjunction with DOW cross-linked polyethylene and tree-retardant cross-linked polyethylene compounds. For other polymer insulation such as EPR and EPDM's, the user is cautioned to establish the utility of DOW ENDURANCE™ HFDA-0801 BK with each formulation.

### Главная Информация

Используется	Высоковольтный полупроводниковый щит
	Полупроводниковый щит
	Подземный Кабель
	Защита кабеля
	Применение проводов и кабелей

Рейтинг агентства	AEIC CS8
	AEIC CS9
	BS 6622
	DIN VDE 0276-620
	DIN VDE 0276-632
	ICEA S-93-639
	ICEA S-94-649
	ICEA S-97-682
	IEC 60502
	IEC 60840
	IEC 62067

ISO 1872 E/BA KHXY 23G200 C40

NF C 33-223

NF C 33-226

UTE C 33-223

Внешний вид	Черный		
Формы	Частицы		
<b>Физический</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Удельный вес	1.14	g/cm <sup>3</sup>	ASTM D792
Экологическое сопротивление растрескиванию (100% Igepal, F0)	> 504	hr	ASTM D1693
<b>Твердость</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Твердость дюрометра (Shore D)	53		ASTM D2240
<b>Механические</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Прочность на растяжение	14.5	MPa	ASTM D638
Удлинение при растяжении (Break)	200	%	ASTM D638
<b>Старение</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Прочность на растяжение-1 неделя (150°C)	98	%	ASTM D638
Коэффициент удлинения-1 неделя (150°C)	90	%	ASTM D638
<b>Тепловой</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Температура ломкости	-40.0	°C	ASTM D746
<b>Электрический</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Сопrotивление громкости			ASTM D991
23°C	15	ohms-cm	ASTM D991
90°C	60	ohms-cm	ASTM D991
130°C	65	ohms-cm	ASTM D991
<b>Дополнительная информация</b>			

Nominal property values above represent tests on molded stress-relieved slabs. Cure times were 15 minutes at 175°C. Extra-Clean Requirements Among many desirable characteristics, DOW ENDURANCE™ HFDA-0801 BK is extra-clean. DOW ENDURANCE™ HFDA-0801 BK typically has less than 0.005% sulfur and less than 0.01% ash. The raw materials used for DOW ENDURANCE™ HFDA-0801 BK are cleaner by design than those used for conventional semiconductive materials. Additional precautions are employed during the manufacture of DOW ENDURANCE™ HFDA-0801 BK relative to conventional conductor shields to prevent introduction of any contamination to the raw materials and to the final product. These low levels of contamination can be expected to play a positive role in the manufacture of a totally extra-clean cable.

#### Supersmooth Extruded Surface

DOW ENDURANCE™ HFDA-0801 BK meets strict standards of smoothness established for a crosslinkable semiconductive shield compound. The extruded surface of DOW ENDURANCE™ HFDA-0801 BK must meet a smoothness specification that is more rigorous than conventional semiconductive shields. Throughout the production process, the product is tested to ensure smoothness. Extruded tapes are scanned by an automatic inspection system in a clean room. The tape smoothness data is managed using an acceptance sampling plan, which ensures that the shipping container meets or exceeds the product's smoothness standard. The DOW ENDURANCE™ HFDA-0801 BK smoothness standard has been designed to meet the global industry specifications for semiconductive shield materials on medium and high voltage cables.

Each batch of DOW ENDURANCE™ HFDA-0801 BK meets the following smoothness requirement:

#### Protrusion Height / Maximum Allowable

60-74 µm / 0 per m<sup>2</sup>

>75 µm / 0 per m<sup>2</sup>

#### Storage

The environment or conditions of storage greatly influences the recommended storage time. Storage should be in accordance with good manufacturing practices. If proper warehousing and storage temperatures [dry conditions, between 50°F and 86°F (10°C and 30°C) in temperature] are utilized, this product may be stored by the customer for up to one year. It is recommended that the practice of using the product on a first-in / first-out basis be established. Storage under extreme conditions may affect the quality, processing, or performance of the product.

Экструзия	Номинальное значение	Единица измерения
Температура сушки	60.0 - 70.0	°C
Время сушки	< 6.0	hr
Температура расплава	121 - 140	°C

#### Инструкции по экструзии

DOW ENDURANCE™ HFDA-0801 BK provides excellent surface finish and outstanding output rates over a broad range of conditions. For optimum results, use melt extrusion temperatures in the suggested range of 250 to 285°F (121 to 140°C) to avoid pre-cure or scorch. Extruder barrel settings of 110°C (230°F) are suggested as a starting point while learning to process DOW ENDURANCE™ HFDA-0801 BK. Specific machine settings will depend on the extruder design and must be established through conventional practices. Dehumidified air hopper drying at 140-160°F (60-70°C) for up to six hours may be employed to remove residual moisture prior to extrusion. Drying is not necessary for DOW ENDURANCE™ HFDA-0801 BK due to the lower moisture absorption characteristics relative to conventional semiconductive products.

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

