

## ELASTOSIL® M 4643 A/B

Silicone

Wacker Chemie AG

### Описание материалов:

Silicone Rubber, RTV-2

Rapid Prototyping, Plastics and Rubber Processing

Rapid Prototyping, Pharmaceuticals & Healthcare

Mold Making, Automotive & Transportation

Rapid Prototyping, Household Care

Mold Making, Composites

Mold Making, Construction

Rapid Prototyping, Automotive & Transportation

Mold Making, Plastics and Rubber Processing

Mold Making, Mold Making

Главная Информация			
Используется	Медицинские/медицинские приложения Изготовление пресс-форм Фармацевтика Прототипирование		
Метод обработки	Литье под давлением реакции (обод)		
Uncured Properties	Номинальное значение	Единица измерения	Метод испытания
Цвет	Grey		
Плотность	1.31	g/cm <sup>3</sup>	ISO 2781
Вязкость	25	Pa·s	ISO 3219
Время отверждения	12	hr	
Срок службы горшка	90	min	
Cured Properties	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore A)	48		ISO 868
Прочность на растяжение	5.00	MPa	ISO 37
Удлинение при разрыве	300	%	ISO 37
Tear Strength	> 10.0	kN/m	ASTM D624B
Linear Shrinkage	< 0.10	%	

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

**Susheng Import & Export Trading Co.,Ltd.**

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

