

## ChronoPrene™ 75A

Thermoplastic Elastomer

AdvanSource Biomaterials Corp.

### Описание материалов:

This biocompatible elastomer may be considered as a substitute for rubber, latex and silicone materials. Soft and compliant, the ChronoPrene resins offer a high flexural modulus, as well as a superior combination of tensile strength and elongation.

An easy molding, high-flow material, ChronoPrene can be processed using conventional extrusion, injection molding and blowmolding methods. Its physical properties make it an optimal material for applications requiring elastic characteristics, such as compliant/ non-compliant balloons, endoscopic and laparoscopic inflation bags.

ChronoPrene can be processed at low temperatures, resulting in excellent surface smoothness and superior elasticity. ChronoPrene exhibits high abrasion resistance, durability and UV stability and is available in hardnesses ranging from 5 Shore A to 75 Shore A.

AdvanSource Biomaterials synthesizes and manufactures medical grade materials offering the ability to tailor physical and mechanical characteristics to support and enhance your end product design.

These mechanical characteristic's, critical to the design and development of medical devices, can incorporate a wide range of physical and chemical properties while maintaining core characteristics such as biodurability and biocompatibility. In most materials, specialized characteristics such as the addition of colorant agents or antimicrobial properties (where applicable) can be added to the polymer to provide a homogenous material and limit secondary processing steps.

In addition, radiopaque agents may also be incorporated into the formula to provide additional product enhancements and may contain up to 40%, by weight, of a radiopaque agent thus allowing varied-scale visibility options.

With an expanding range of secondary operations including custom solution development, prototype coating capabilities, and project management services, ASB's expert team of chemists, scientists, engineers and industry professionals assist in every stage of customers' projects, from concept initiation through full-scale manufacture.

### Главная Информация

Характеристики	Биосовместимый Прочный Хорошая стойкость к истиранию Хорошая химическая стойкость Хорошая плавность Хорошая поверхность Хорошая устойчивость к ультрафиолетовому излучению Высокое удлинение Высокий поток Гидрофобный Нет животных производных компонентов Мягкий
Используется	Медицинские/медицинские приложения
Рейтинг агентства	ISO 10993 часть 5 USP класс VI
Формы	Гранулы
Метод обработки	Выдвухное формование

Экструзия

Литье под давлением

Физический	Номинальное значение	Единица измерения	Метод испытания
Массовый расход расплава (MFR) (200°C/5.0 kg)	2.0 to 26	g/10 min	ASTM D1238
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра (Shore A)	75		ASTM D2240
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение			ASTM D638
Break	8.27 to 9.65	MPa	
50% Strain	5.69 to 6.72	MPa	
100% Strain	6.72 to 7.58	MPa	
200% Strain	7.58 to 8.96	MPa	
300% Strain	8.96 to 9.65	MPa	
Удлинение при растяжении (Break)	250 to 350	%	ASTM D638
Инъекция	Номинальное значение	Единица измерения	
Температура сушки-Осушитель сушилка	71.1 to 93.3	°C	
Время сушки-Осушитель сушилка	3.0 to 4.0	hr	
Dew Point	-40.0	°C	
Рекомендуемая максимальная влажность	0.050	%	

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat