

Styropor® P 326 M

Expanded Polystyrene

BASF Corporation

Описание материалов:

Application

For the production of expanded foam moldings having a wall thickness of at least 8 mm with very good mechanical properties. Expanded foam made from Styropor® P 326 M exhibits mechanical properties which go beyond those of expanded foam made from P 326, especially with regard to flexural strength.

Product description

Expandable polystyrene (EPS) (blowing agent: pentane).

Главная Информация		
Добавка	Дующий агент 2	
Используется	Пена	
Рейтинг агентства	EC 1907/2006 (REACH)	
Соответствие RoHS	Соответствует RoHS	
Формы	Сферы	
Физический	Номинальное значение	Единица измерения
Видимая плотность	0.02	g/cm ³
Анализ сита		
< 500.0 µm	< 2.0	%
500.0 to 1000.0 µm	> 93	%
> 1.00 mm	< 5.0	%
Старение-Промежуточный	10.0 to 24.0	hr
Bead Size	700.0 to 900.0	µm

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

