

Ad-Tech Epoxy EC-405 (55R/45H)

Epoxy; Epoxide

Ad-Tech Plastic Systems Corp.

Описание материалов:

Ad-Tech Epoxy EC-405 (55R/45H) is an Epoxy; Epoxide (Epoxy) product. It can be processed by casting and is available in North America. Applications of Ad-Tech Epoxy EC-405 (55R/45H) include coating applications and engineering/industrial parts.

Characteristics include:

Good Aesthetics

Wear Resistant

| Главная Информация | | | |
|-----------------------------------|--|-------------------|-----------------|
| Характеристики | Хорошая стойкость к истиранию Хорошая поверхность | | |
| Используется | Ламинаты Машина/механические детали | | |
| Внешний вид | Янтарь | | |
| Формы | Гранулы | | |
| Метод обработки | Литье | | |
| Физический | Номинальное значение | Единица измерения | Метод испытания |
| Видимая плотность | 1.10 | g/cm ³ | ASTM D1895 |
| Твердость | Номинальное значение | Единица измерения | Метод испытания |
| Твердость дюрометра (Shore D) | 65 | | ASTM D2240 |
| Термокомплект | Номинальное значение | Единица измерения | Метод испытания |
| Компоненты термокомплекта | | | |
| Hardener | Mix Ratio by Weight: 55 | | |
| Resin | Mix Ratio by Weight: 45 | | |
| Срок службы горшка (25°C) | 25 to 30 | min | |
| Терморегулирующая вязкость (25°C) | 950 | cP | ASTM D2393 |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

