

ELASTOSIL® RT 745 A/B

Silicone

Wacker Chemie AG

Описание материалов:

Silicone Rubber, RTV-2

Electronic Control Devices, Automotive & Transportation

Electronic Control Devices, Electronics

Electronic Control Devices, Electrical Industry

Elect. Control Devices/Protect Sensors, Electronics

Elect. Control Devices/Protect Sensors, Automotive & Transportation

Bonding & Sealing, Lighting

Bonding & Sealing, Mechanical and Plant Engineering

Bonding & Sealing, Adhesives and Sealants

Bonding & Sealing, Renewable Energies

Главная Информация

| | |
|-----------------|---|
| Используется | Электрическое/электронное применение Полупроводниковые защитные покрытия |
| Метод обработки | Инкапсулирование Полировка |

| Uncured Properties | Номинальное значение | Единица измерения | Метод испытания |
|--------------------|----------------------|-------------------|-----------------|
| Цвет | Translucent | | |
| Плотность | 0.970 | g/cm ³ | ISO 2781 |
| Вязкость | 1.0 | Pa·s | ISO 3219 |
| Срок службы горшка | > 240 | min | |

| Cured Properties | Номинальное значение | Единица измерения | Метод испытания |
|-----------------------------|----------------------|-------------------|-----------------|
| Твердость по суше (Shore A) | 15 | | ISO 868 |
| Относительная проницаемость | 2.50 | | IEC 60250 |
| Сопrotивление громкости | 1.0E+15 | ohms-cm | IEC 60093 |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519
Мобильный телефон: +86-13424755533
Email: sales@su-jiao.com
Адрес: Господин Чжао
Район Фэнсянь, Шанхай, Китай

