

Baoding 6126H

Thermoplastic Polyurethane Elastomer

Baoding Bangtai Polymeric New-Materials Co.,Ltd

Описание материалов:

Properties: Hot melt adhesive film. It can also be used with MEK and EAC when dissolved. Also with high crystallization rate and especially has great bonding capacity with TPU, PVC, NYLON, and fabric.

Applications: Application: Fire hose, Shoe, Water seal, Ink print, Anti-explosion glass used into the high buildings.

Главная Информация		
Характеристики	Bondability	
	Хорошая адгезия	
Используется	Клеи	
	Обувь	
	Шланг	
	Печатные чернила	
	Уплотнения	
Внешний вид	Белый	
Физический	Номинальное значение	Единица измерения
Вязкость раствора ¹	3600 to 4200	mPa·s
Тепловой	Номинальное значение	Единица измерения
Викат Температура размягчения	55.0 to 65.0	°C
Дополнительная информация	Номинальное значение	Единица измерения
Flow Beginning Temperature	90 to 100	°C

NOTE

1. 15% solid content in MEK

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

