

Vinnolit® E 70 LF

Polyvinyl Chloride

Vinnolit GmbH & Co. KG

Описание материалов:

PVC for paste application

@ Vinnolit E 70 LF is a fine-particle, paste- making copolymer of vinyl chloride and 5 % vinyl acetate yielding low viscosity plastisols with an excellent storage stability (see diagram).

Due to its vinyl acetate content, Vinnolit E 70 LF can be easily processed at lower gelling temperatures.

Processing and Application:

Vinnolit E 70 LF may be converted into pastes by the standard methods, by dissolver or low- speed mixer. However, undue heating of the paste during mixing should be avoided since the vinyl acetate content may cause a rise in viscosity. Pastes based on Vinnolit E 70 LF can be applied by all the usual procedures. Vinnolit E 70 LF is a low temperature gelling, low-viscosity paste grade, recommended for coating heat-sensitive base fabrics, laminating pastes, carpet backings as well as automotive underbody and seam sealants. These applications also benefit from a high filler-loading capability as well as good adhesion to textile base fabrics and automotive metal surfaces. To lower paste viscosity and increase shelf life, Vinnolit E 70 LF may be blended with homopolymer extender resins such as Vinnolit EXT / Vinnolit C 65 V.

Remarkable properties are:

significant lower gelling temperatures

good adhesion at textiles and automotive metal sheets

better mechanical properties

better abrasion resistance in UBC-mastics

excellent storage stability of plastisols

Главная Информация

Характеристики	Сополимер		
	Хорошая стойкость к истиранию		
	Хорошая адгезия		
	Низкая вязкость		
Используется	Автомобильные Приложения		
	Ковровая подложка		
	Нанесение покрытия		
	Ламинаты		
	Герметики		
Метод обработки	Пластик		
Физический	Номинальное значение	Единица измерения	Метод испытания
Видимая плотность	0.40	g/cm ³	ISO 60
K-Value	70.0		ISO 1628-2
Распределение размеров частиц-Сохранение сита ¹	< 3.0	%	
Виниловый материал-Ацетат	5.0	%	
Летучее вещество	< 0.50	%	ISO 1269
NOTE			

1. retained on 0.063 mm screen

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat