

## North American Santicizer® 148

Plasticizer Additive

Ferro Corporation

### Описание материалов:

Santicizer® 148 Plasticizer is an efficient flame retardant, excellent for many commercial resins, particularly Polyvinyl Chloride and its copolymers, Polyvinyl Acetate and Acrylics. It is high solvating and provides good low-temperature flexibility, and it is miscible with most common solvents. Santicizer® 148 imparts flame retardance, low-temperature flexibility and low volatility in Polyvinyl Chloride. It can replace DOP part-for-part to the level needed for fire retardancy while maintaining the flexibility and the softening efficiency of that phthalate. Its use in the compound imparts low smoke generation performance that is far superior to Triaryl Phosphates or Antimony Oxide. It also offers superior fusion properties and solvating action and imparts resistance to abrasion, oil and grease. Used as a 10%-15% replacement for phthalates, it imparts excellent weather and light stability. Hand and drape of the finished film or coated fabric containing Santicizer® 148 are outstanding.

In vinyl plastisols, Santicizer® 148 exhibits fast fusion, low initial viscosity and moderate viscosity stability. Cell structure of vinyl foams is excellent. Clear formulations show a sparkling clarity with Santicizer® 148. The cured compound possesses good low-temperature flexibility and flame retardance.

Santicizer® 148 offers PVC adhesives - such as laminating adhesives - fast fusion, good viscosity and flame retardance. When laminating PVC film to cloth, the use of a fire-retardant adhesive dramatically reduces the flammability of the laminate.

By the addition of Silica Aerogel and a non-ionic detergent, a shear-sensitive gel of Santicizer® 148 can be applied to expanded-glass air filters. Such treated filters are flame retardant and efficient dust collectors.

Santicizer® 148 is an efficient low volatility solvator for Ethyl Cellulose, Nitrocellulose, SBR and Nitrile (Buna N) rubbers.

Главная Информация		
Additives Physical	Номинальное значение	Единица измерения
Плотность	1.07	g/cm <sup>3</sup>
Boiling Temperature	245	°C

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

### Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

