

Dugdale PVC Static Flexible PVC Nitrile Compound

Flexible Polyvinyl Chloride

Dugdale Plc

Описание материалов:

Static gasket compound (BPF 345/2 specification).

This compound has been developed for ease of processing on both co-extrusion and post co-extrusion equipment. Set up conditions of 150 °C flat are typically used although this may vary depending on the end users process.

Главная Информация			
Характеристики	Хорошая гибкость		
Используется	Прокладки		
Формы	Гранулы		
Метод обработки	Кокстружия		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.35	g/cm ³	BS 2782 620A
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore A)	58 to 62		
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение	11.5	MPa	BS 2782 320A
Удлинение при растяжении (Break)	350	%	BS 2782 320A
Дополнительная информация	Номинальное значение	Метод испытания	
Softening Range	63.0	BS 2782 365A	

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

