

Europrene® N 2860 GRN

Acrylonitrile Butadiene Rubber

Versalis S.p.A.

Описание материалов:

Europrene® N 2860 GRN is an advanced technology cold polymerized acrylonitrile-butadiene copolymer made at the PortoTorres production facility in Italy. A non staining antioxidant is added during the production process.

Europrene® N 2860 GRN is characterised by excellent processability and tear resistance at high temperature, good dimensional stability both in calendaring and in extrusion. GRN grades show higher cure rate, higher low temperature flexibility, higher crosslinking density and better mechanical properties, better oil and fuel resistance in comparison to STD grades. The improved processability guarantees low mould fouling products and then long production runs, lower mould wear

and less production controls. The vulcanization can be performed by sulphur based systems or by peroxides. The low temperature properties can be improved by adding polar plasticizers as synthetic esters of adipic, sebacic or phtalic acids. To improve heat, light and ozone resistance, suitable protective agents as amine or phenolic antioxidants have to be added in the compounding process.

Grade with faster cure rate compared to equivalent standard type. Suitable for injection applications (low mould fouling)

Главная Информация			
Добавка	Антиоксидант		
Характеристики	Антиоксидант		
	Быстрое лечение		
	Топливная устойчивость		
	Хорошая стабильность размеров		
	Хорошая технологичность		
	Хорошая прочность на разрыв		
	Гибкость при низкой температуре		
	Маслостойкий		
Внешний вид	Желтый		
Формы	Тюк		
Метод обработки	Литье под давлением		
Физический	Номинальное значение	Единица измерения	Метод испытания
Вязкость Mooney (ML 1+4, 100°C)	60	MU	ASTM D1646
Acrylonitrile Content	28.0	wt%	ASTM D3533
Содержание золы	< 0.5	wt%	ASTM D5667
Органическая кислота	< 0.5	wt%	ASTM D5774
Мыло	< 0.6	wt%	ASTM D5774
Летучее вещество	< 0.70	wt%	ASTM D5668

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

