

ALKAMIX™ MB-AO300

Unspecified

Marplex Australia Pty. Ltd.

Описание материалов:

ALKAMIX™ MB-AO300 is BHT (Butylated Hydroxy Toluene) free antioxidant masterbatch designed to impart thermal processing stability to base grade low density polyethylene during extrusion.

ALKAMIX™ MB-AO300 can be added to base grade low density polyethylene during extrusion to assist in overcoming thermal instability problems. The level required will vary according to the type of extrusion, conditions and polymer used, however the recommended addition level is between 1 and 2 percent.

ALKAMIX™ MB-AO300 can also be used as a shutdown compound to prevent oxidation of polymer left idle in an extruder. As a shutdown compound, it is usually added at concentrations of 30 percent or more to fractional MFI low density polyethylenes.

The maximum level of addition of ALKAMIX™ MB-AO300 based on both good manufacturing practice and to ensure conformance to the requirements to the United States Food and Drug Administration Regulations CFR21 is 4 percent, when added to a polyethylene formulation free of any other additives. The suitability of finished articles manufactured using this material as a component, and the observance of given limitations, must be verified by the converter for each application to ensure compliance with all relevant regulations. An overall migration limit may apply to the finished article.

Главная Информация

| Добавка | Антиоксидант | | |
|----------------------------------|----------------------|-------------------|-----------------|
| Характеристики | Антиоксидант | | |
| Используется | Маточная смесь | | |
| Физический | Номинальное значение | Единица измерения | Метод испытания |
| Плотность | 0.920 | g/cm ³ | ASTM D1505 |
| Инъекция | Номинальное значение | Единица измерения | |
| Температура обработки (расплава) | < 200 | °C | |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat