

Shandong PP PGF6301

30% стекловолокно

Polypropylene

Shandong Dongchen Engineering Plastics Co., Ltd.

Описание материалов:

Shandong PP PGF6301 is a Polypropylene material filled with 30% glass fiber. It is available in Asia Pacific.

Important attributes of Shandong PP PGF6301 are:

Flame Rated

Flame Retardant

Good Processability

Typical applications include:

Appliances

Electrical/Electronic Applications

Главная Информация	
Наполнитель/армирование	Стекловолокно, 30% наполнитель по весу
Добавка	Огнестойкий
Характеристики	Огнестойкий Хорошая технологичность
Используется	Приборы Электрическое/электронное применение

Механические	Номинальное значение	Единица измерения
Tensile Stress (Yield)	60.0	MPa
Растяжимое напряжение (Break)	3.0	%
Флекторный модуль	4500	MPa
Флекторный стресс	90.0	MPa

Воздействие	Номинальное значение	Единица измерения
Ударная прочность	10	kJ/m ²
Charpy Unnotched Impact Strength	30	kJ/m ²

Воспламеняемость	Номинальное значение	Метод испытания
Огнестойкость	V-0	UL 94

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

