

## SOLPLAST TV 10000A

Styrene Ethylene Ethylene Propylene Styrene Block Copolymer

UTEKSOL d.o.o.

### Описание материалов:

Is a commercial name for thermoplastic vulkanisers (TPE - V) based on S EEP S block copolymers, mixed with PP and enmeshed to the certain degree.

Resistance to acid, bases and all aqueous solutions is excellent.

Resistance to alcohol and glycols is very good.

Resistance to fat and of oil is good.

Resistance to aromatic hydrocarbons is bad.

All "SOLPLASTS" have a good electric-volume resistance: thats more then 1e12 ohm-cm.

SERIES 10000

Technical compounds based on SEEPS block copolymers

Different phisical characteristics and optics considering purpose of use.

Work temperature between -50 and +120°, shortly up to 150°C.

Because of saturated chemical structure and partly enmeshed structure of elastomer are suitable for wide range of articles, where high temperature subsistence and stability to the light is required, as to the rest atmospheric impacts.

SERIES 1000

Transparent and half transparent (crep) compound

Extended or company realization

Suitable for more demanding roles

Главная Информация			
Характеристики	Кислотоупорный Устойчивость к воздействию алкоголя Устойчивость к основанию Высокая термостойкость Стабилизированный свет		
Используется	Оптическое применение		
Внешний вид	Прозрачный/прозрачный		
Метод обработки	Литье под давлением		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	0.930 to 1.06	g/cm <sup>3</sup>	ISO 1183
Массовый расход расплава (MFR)	10 to 20	g/10 min	ISO 1133
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore A)	40 to 80		ISO 868
Эластомеры	Номинальное значение	Единица измерения	Метод испытания
Комплект сжатия			ISO 815
72°C, 23 hr	25 to 35	%	
120°C, 23 hr	30 to 40	%	

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

