ExxonMobil™ LLDPE LL 6201.19

Linear Low Density Polyethylene Resin

ExxonMobil Chemical

Описание материалов:

LL 6201 is a butene copolymer with narrow molecular weight distribution, developed for thin-walled parts with high requirements for easy processability. The resin has been developed with toughness and tear resistance suitable for frozen food packaging applications.

Главная Информация			
Физический	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Массовый расход расплава (MFR) (190°C/2.16 kg)	50	g/10 min	ASTM D1238
Экологическое сопротивление растрескиванию (10% Igepal, F50)	27.0	hr	ASTM D1693B
Механические	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Прочность на растяжение (Yield)	11.9	MPa	ASTM D638
Флекторный модуль			ASTM D790B
1% secant	469	MPa	ASTM D790B
2% secant	420	MPa	ASTM D790B
Тепловой	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Викат Температура размягчения	84.8	°C	ASTM D1525
Пиковая температура плавления	122	°C	ASTM D3418
Дополнительная информация			
□□□□□□□□□□.□□□□□□□□□□□□□□□□□□□□.			
Юридическое заявление			
□□□□□□□□□□□□□,□□□□□□□□□□□□□□□□□□□

WeChat