

LUVOCOM® 80-7727

Углеродное волокно

Acetal (POM) Copolymer

Lehmann & Voss & Co.

Описание материалов:

LUVOCOM®80-7727 is a polyoxymethylene (POM) copolymer material, and the filler is carbon fiber reinforced material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM®The main features of 80-7727 are:

Conductivity

Electrostatic protection

Good dimensional stability

Good stiffness

Typical application areas include:

textile/fiber

engineering/industrial accessories

Automotive Industry

business/office supplies

Главная Информация				
Наполнитель/армирование	Армированный материал из углеродного волокна			
Характеристики	Хорошая стабильность размеров			
	Проводящий			
	Жесткий, хороший			
	Защита от электростатического разряда			
Используется	Хорошая прочность			
	Текстильные изделия			
	Инженерные аксессуары			
	Применение в автомобильной области			
Внешний вид	Бизнес-оборудование			
	Натуральный цвет			
	Физический	Номинальное значение	Единица измерения	Метод испытания
	Плотность	1.46	g/cm ³	ISO 1183
Формовочная усадка	0.10 - 0.40	%	DIN 16901	
Поглощение воды (23°C, 24 hr)	< 0.10	%		
Механические	Номинальное значение	Единица измерения	Метод испытания	
Модуль растяжения	19000	MPa	ISO 527-2	
Tensile Stress (Break)	130	MPa	ISO 527-2	
Растяжимое напряжение (Yield)	1.3	%	ISO 527-2	
Флекторный модуль	16000	MPa	ISO 178	

Флекторный стресс	185	MPa	ISO 178
Коэффициент трения			
Dynamic	0.15		
Static	0.11		
Flexural Strain at Flexural Strength	1.8	%	ISO 178
Максимальная рабочая температура-Короткий срок	120	°C	
Insulation Resistance		ohms	IEC 60167
Воздействие	Номинальное значение	Единица измерения	Метод испытания
Charpy Unnotched Impact Strength (23°C)	30	kJ/m ²	ISO 179/1eU
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура непрерывного использования	100	°C	UL 746B
Викат Температура размягчения	160	°C	ISO 306/A
Электрический	Номинальное значение	Единица измерения	Метод испытания
Удельное сопротивление поверхности	< 1.0E+2	ohms	IEC 60093
Иньекция	Номинальное значение	Единица измерения	
Температура сушки			
A	75.0	°C	
Dehumidification desiccant, B	120	°C	
Время сушки			
A	2.0 - 8.0	hr	
Dehumidification desiccant, B	2.0 - 4.0	hr	
Задняя температура	175 - 190	°C	
Средняя температура	185 - 205	°C	
Передняя температура	180 - 200	°C	
Температура сопла	175 - 200	°C	
Температура обработки (расплава)	200	°C	
Температура формы	80.0 - 120	°C	
Инструкции по впрыску			

General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

If originally sealed containers are used, it is normally possible to omit the predrying stage. If PTFE materials are not predried, an increase in deposits inside the mould may occur. When changing from higher melting-point polymers such as polyamides to this product, extremely thorough intermediate cleaning should be carried out. Processing temperatures above 215°C may very rapidly cause thermal damage and should therefore be avoided, particularly as formaldehyde may be eliminated here.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

Please contact us for further information.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

