

## HFDB-4201 SC sb K

Crosslinked Polyethylene

The Dow Chemical Company

### Описание материалов:

HFDB-4201 SC sb K is a long-life, cross linkable, low-density, polyethylene insulation compound of high cleanliness and purity developed especially for the insulation of High Voltage power cables. HFDB-4201 SC sb K is 100% pellet checked, decreasing the risk against singular large contaminants. HFDB-4201 SC sb K is equipped with a non-migrating stabilizer providing high thermal stability, long term storage stability, and optimum cross-linking behavior.

Applications:

HFDB-4201 SC sb K is recommended especially for the insulation of High Voltage submarine cables, as well as for high stress underground cable designs, <= 220kV.

Specifications:

Cables insulated with HFDB-4201 SC sb K would be expected to meet the requirements in the following standards when processed using state-of-the-art cable manufacturing practices:

IEC: 62067, 60840

CENELEC: HD 632 S2

AEIC: CS9

ANSI/ICEA: 108-720-2004

GB/T 11017, GB/T 18890

Главная Информация			
Используется	Сверхвысоковольтная изоляция Высоковольтная изоляция		
Рейтинг агентства	AEIC CS9 IEC 60840 IEC 62067		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	0.920	g/cm <sup>3</sup>	ISO 1183
Массовый расход расплава (MFR) <sup>1</sup> (190°C/2.16 kg)	2.1	g/10 min	ISO 1133
Влага <sup>2</sup>		ppm	Internal method
Термокомплект <sup>3</sup>			IEC 811-2-1
Elongation under Load : 200°C		%	IEC 811-2-1
Permanent Deformation : 200°C		%	IEC 811-2-1
Готферт эластограф	4.4	lb-in	ISO 6502
Метанол для мытья			Internal method
Insoluble part		ppm	Internal method
Soluble part		ppm	Internal method
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение	20.0	MPa	IEC 60811-1-1
Удлинение при растяжении (Break)	500	%	IEC 60811-1-1

Старение	Номинальное значение	Единица измерения	Метод испытания
Изменение прочности на растяжение <sup>4</sup>	< 25	%	IEC 60811-1-2
Изменение максимального удлинения <sup>5</sup>	< 25	%	IEC 60811-1-2

Электрический	Номинальное значение	Единица измерения	Метод испытания
Сопrotивление громкости	> 1.0E+16	ohms-cm	IEC 60093
Диэлектрическая прочность	> 30	kV/mm	IEC 60243-1
Диэлектрическая постоянная (1 MHz)	< 2.30		IEC 60250
Коэффициент рассеивания (50 Hz)	< 3.0E-4		IEC 60250

Дополнительная информация	Номинальное значение	Единица измерения	Метод испытания
---------------------------	----------------------	-------------------	-----------------

#### Cleanliness:

High cleanliness is assured through a number of precautions taken during the manufacturing of DOW HFDB-4201 SC sb K

The specifications are set to exclude contaminants >100µm

These specifications are based on online continuous sampling and testing

HFDB-4201 SC sb K is a 100% pellet checked product

#### Storage:

The environment or conditions of storage greatly influences the recommended storage time. Storage under extreme conditions may affect the quality, processing, or performance of the product. Storage should be in accordance with good manufacturing practices. The recommended storage conditions are dry conditions with temperatures between 50°F and 86°F (10°C and 30°C). When stored under these conditions, the product may be used by the customer for up to one year from the date of sale or two years from the date of manufacture, whichever comes first. It is recommended that the practice of using the product on a first-in / first-out basis be established.

#### Packaging:

HFDB-4201 SC sb K can be delivered in 500kg UNICLEAN™ big bags or in 1000kg bottom unloading octabins

#### Инструкции по экструзии

HFDB-4201 SC sb K provides outstanding output rates over a broad range of conditions. For optimum results, melt extrusion temperatures of ≤ 135°C are recommended for submarine applications.

Screen packs are only required if there is a need to improve the homogenization of the melt or as protection from contamination entering during unloading and processing. HFDB-4201 SC sb K allows the use of fine mesh screens. Specific recommendations for processing conditions can be determined when the application and processing equipment type are known.

At start-up, it is recommended to use DFDK-4850 start-up compound to achieve stable extruder conditions.

#### NOTE

1.	Base Resin
2.	Karl Fischer titration
3.	0.2 MPa
4.	after 10 days aging at 150°C
5.	after 10 days aging at 150°C.

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

