

## ALKAMIX™ MB-SAMBA

Unspecified

Marplex Australia Pty. Ltd.

### Описание материалов:

ALKAMIX™ MB-SAMBA is a slip masterbatch formulated with Erucamide at a concentration of 2%.

ALKAMIX™ MB-SAMBA can be added to polyethylene during extrusion to reduce the coefficient of friction of films. The level required will vary according to coefficient of friction desired, gauge of film, polymer type (LLDPE, LDPE, etc...) and other factors such as the presence of other additives (including antiblocks, colourants / pigments, etc...). For injection moulded articles, typical addition rates of MB-SAMBA of up to 2.0% are recommended due to the thickness of the moulded article. Higher addition rates may result in problems with printing or label adhesion, or possibly warpage.

The maximum level of addition of ALKAMIX™ MB-SAMBA based on both good manufacturing practice and to ensure conformance to the requirements to the United States Food and Drug Administration Regulations CFR21 is the minimum required to achieve the desired effect. When added to a polyethylene formulation free of any slip additives, the maximum recommended level is 10%. The suitability of finished articles manufactured using this material as a component, and the observance of given limitations, must be verified by the converter for each application to ensure compliance with all relevant regulations. An overall migration limit may apply to the finished article.

Главная Информация			
Добавка	Эрукамид скольжения (2%)		
Характеристики	Комбинация		
Используется	Маточная смесь		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	0.922	g/cm <sup>3</sup>	ASTM D792
Инъекция	Номинальное значение	Единица измерения	
Температура обработки (расплава)	200	°C	

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

### Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat