

TPV Elastoprene® N87A-S

Polypropylene + EPDM Rubber

ELASTORSA Elastomeros Riojanos S.A.

Описание материалов:

Dynamically vulcanized thermoplastic (TPV) is a particular type of thermoplastic elastomer (TPE) which offers much better results given the exclusive combination of an elastomeric phase deeply dispersed in a continuous thermoplastic phase.

TPV Elastoprene® is a mixture of polypropylene and dynamically vulcanised EPDM rubber (PP/EPDM), with properties similar to those of other rubber products but with better results than traditional plastic materials.

Due to the enormous advantages of processability, vulcanized rubber materials are being substituted by TPV Elastoprene®, using the traditional technology in the transformation of plastic. Furthermore, with the excellent properties obtained, TPV Elastoprene® is replacing plastic materials like PVC.

TPV Elastoprene® is completely recyclable and reusable, safe to the environment, thus improving the overall profitability of the process; an added advantage to rubber production and manufacture.

TPV Elastoprene® has good resistance to the effects of the ozone, UV and diverse chemical products, with an operating temperature from -60 to 135°C.

APPLICATIONS

The excellent properties of this material make it ideal to satisfy the demanding requirements of the automobile sector, due to its response to temperature and compression set deformation. It can be used in both the inner and outer part of the vehicle.

Its principle application is for hollow parts which, given their shape, are manufactured via blow molding: such as bellows or conductions pipes.

Главная Информация

Характеристики	Хорошая устойчивость к ультрафиолетовому излучению Перерабатываемые материалы Озоновая защита Хорошая химическая стойкость		
Используется	Применение выдувного формования Трубопроводная система Применение в автомобильной области		
Внешний вид	Черный		
Формы	Частицы		
Метод обработки	Выдувное формование		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	0.950	g/cm³	ISO 1183
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра (Shore A, 5 sec, 2.00 mm, Injection Molded)	87		ISO 868
Эластомеры	Номинальное значение	Единица измерения	Метод испытания
Tensile Stress (100% Strain, 2.00 mm)	7.50	MPa	ISO 37
Tensile Stress (Yield, 2.00 mm)	13.0	MPa	ISO 37
Удлинение при растяжении (Break, 2.00 mm)	500	%	ISO 37

Tear Strength (23°C, 2.00 mm)	29	kN/m	ISO 34-1
Комплект сжатия (70°C, 22 hr)	48	%	ISO 815
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура ломкости	-51.0	°C	ISO 812
Экструзия	Номинальное значение	Единица измерения	
Температура сушки	80.0	°C	
Время сушки	2.0	hr	
Температура расплава	180 - 215	°C	
Температура матрицы	200 - 230	°C	

Инструкции по экструзии

Recommended Scrap: 20%

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat