

Maxxam™ FR PE126 BLK 3330

Low Density Polyethylene

PolyOne Corporation

Описание материалов:

Maxxam™ FR flame-retardant polyolefin compounds and masterbatches meet stringent flammability performance requirements defined by industry agencies, including Underwriters Laboratories UL 94 V-2, V-0, and 5VA performance ratings. In addition, many compounds in the Maxxam FR portfolio offer elevated Relative Thermal Index (RTI) ratings.

Главная Информация			
Характеристики	Огнестойкий		
Внешний вид	Черный		
Формы	Гранулы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	0.998	g/cm ³	ASTM D792
Массовый расход расплава (MFR) ¹ (190°C/2.16 kg)	0.30	g/10 min	ASTM D1238
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение ² (Yield)	15.9	MPa	ASTM D638
Удлинение при растяжении ³ (Break)	140	%	ASTM D638
Воспламеняемость	Номинальное значение	Метод испытания	
Огнестойкость (1.59 mm)	V-2	Internal Method	

NOTE	
1.	Procedure A
2.	Type I, 51 mm/min
3.	Type I, 51 mm/min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

