

Eastar™ AN001, Natural

Copolyester

Eastman Chemical Company

Описание материалов:

Eastar™ AN001 Copolyester has excellent appearance and is nearly water-clear. Its most outstanding features are its chemical resistance and processing capabilities. Exposure to aromatic oils often causes crazing or actual fracture of many polymer resins, but AN001 maintains its physical properties when exposed to these oils, and its appearance is virtually unchanged.

This product has been GREENGUARD INDOOR AIR QUALITY CERTIFIED®.

The GREENGUARD INDOOR AIR QUALITY CERTIFIED® Mark is a registered certification mark used under license through the GREENGUARD Environmental Institute (GEI). GEI is an industry-independent, non-profit organization that oversees the GREENGUARD Certification Program. The GREENGUARD Certification Program is an industry independent, third-party testing program for low-emitting products and materials for indoor environments. For more information about GEI and to obtain printable certificates for Eastman™ Copolyesters, visit www.greenguard.org. Choose Eastman Chemical Company under the Manufacturer category and click search to display a list of our products.

This product has been CRADLE TO CRADLE CERTIFIED(cm)

The CRADLE TO CRADLE CERTIFIED(cm) Mark is a registered certification mark used under license through McDonough Braungart Design Chemistry (MBDC). MBDC is a global sustainability consulting and product certification firm. The CRADLE TO CRADLE® framework moves beyond the traditional goal of reducing the negative impacts of commerce ('eco-efficiency'), to a new paradigm of increasing its positive impacts ('eco-effectiveness'). At its core, Cradle to Cradle design perceives the safe and productive processes of nature's 'biological metabolism' as a model for developing a 'technical metabolism' flow of industrial materials. Product components can be designed for continuous recovery and reutilization as biological and technical nutrients within these metabolisms. For more information about MBDC and to obtain printable certificates for Eastman Copolyesters, visit <http://www.mbdc.com>.

Главная Информация

UL YellowCard	E118289-220107
Характеристики	Барьерная смола Отличная Печатающая способность Хорошая химическая стойкость Хорошая цветность Хорошая ударпрочность Хорошая технологичность Хорошая жесткость Хорошая прочность Высокая четкость Глянцевый
Используется	Косметическая упаковка Упаковка Персональный уход
Внешний вид	Натуральный цвет
Формы	Гранулы
Метод обработки	Экструзия Литье под давлением

Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.20	g/cm ³	ASTM D792
Формовочная усадка-Поток (3.20 mm)	0.20 to 0.60	%	ASTM D955
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость Роквелла (R-Scale, 23°C)	103		ASTM D785
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение			ASTM D638
Yield, 23°C	47.0	MPa	
Break, 23°C	51.0	MPa	
Удлинение при растяжении			ASTM D638
Yield, 23°C	5.0	%	
Break, 23°C	320	%	
Флекторный модуль (23°C)	2000	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	69.0	MPa	ASTM D790
Воздействие	Номинальное значение	Единица измерения	Метод испытания
Зубчатый изод Impact			ASTM D256
-40°C	40	J/m	
23°C	80	J/m	
Незубчатый изод Impact			ASTM D4218
-40°C	No Break		
23°C	No Break		
Ударное устройство для дротиков			ASTM D3763
-40°C, Energy at Peak Load	48.0	J	
23°C, Energy at Peak Load	42.0	J	
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура отклонения при нагрузке			ASTM D648
0.45 MPa, Unannealed	73.0	°C	
1.8 MPa, Unannealed	65.0	°C	
Оптический	Номинальное значение	Единица измерения	Метод испытания
Коэффициент пропускания			ASTM D1003
Total	91.0	%	
Regular	89.0	%	
Haze	0.30	%	ASTM D1003
Инъекция	Номинальное значение	Единица измерения	Метод испытания
Температура сушки	70.0	°C	
Время сушки	3.0	hr	
Температура обработки (расплава)	230 to 280	°C	
Температура формы	15.0 to 30.0	°C	

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

