

BIOPLAST® 200

Thermoplastic

BIOTEC GmbH & Co. KG

Описание материалов:

BIOPLAST 200 is the brand name of BIOTEC for an entirely new kind of plasticizer free thermoplastic material. Therefore there are no deposits or vapors by softening during processing of BIOPLAST 200th The material is suitable for blown film extrusion, cast film extrusion, profile extrusion and injection molding of completely biodegradable products. The biodegradability and other functional properties enable the converter into product areas vorzu-penetrate to the traditional thermoplastic materials were previously inaccessible. The potato starch used in BIOPLAST 200 is not, as in the case of thermoplastic Starch (TPS), mixed with plasticizers, but the original, native Condition incorporated into the material. BIOPLAST 200 is therefore produced by superior processing and performance characteristics combined with excellent storage ability of.

Главная Информация	
Характеристики	Биоразлагаемый Содержание возобновляемых ресурсов
Используется	Сумки Нанесение покрытия Пленка Пищевая упаковка Пищевая упаковка Сетка Бумажные Покрытия Лист Термоусадочная пленка
Рейтинг агентства	RU 13432 EC 2002/72/EC EC 67/548/EEC
Внешний вид	Прозрачный/прозрачный
Формы	Гранулы
Метод обработки	Выдувная пленка Литая пленка Экструзионная пленка Литье под давлением Экструзионный профиль

Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	1.32	g/cm ³	ISO 1183/A

Видимая плотность	0.78	g/cm ³	ISO 60
Массовый расход расплава (MFR) (190°C/5.0 kg)	2.4	g/10 min	ISO 1133
Размер частиц	2.50	mm	
Содержание воды	< 0.50	%	Internal Method
Анализ заполнения	Номинальное значение	Единица измерения	Метод испытания
Melt Density	1.18	g/cm ³	ISO 1133

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

