

Eltex® P KS399

Polypropylene Random Copolymer

INEOS Olefins & Polymers Europe

Описание материалов:

Benefits & Features

Eltex® P KS399 belongs to INEOS' third generation of heat seal resin and is based on the new structural concept developed for the 2nd generation terpolymer (Eltex® P KS350 series) and is successfully used by major BOPP film producers all over the world.

Eltex® P KS399 is a propylene/alpha olefin copolymer specially developed for the sealing layers of "coextruded bioriented film" for food and technical packaging. It provides a unique combination of extremely low sealing temperature (90°C) and improved ease of processing, yet maintaining excellent optical properties.

Specially developed for the sealing layers of "coextruded bioriented film" for food and technical packaging

Extremely low sealing temperature (90°C)

Ease of processing (Melting point >130°C)

Applications

Barefoot copolymer specially developed for the sealing layers of "coextruded bioriented film"

Главная Информация			
Характеристики	Сополимер Приемлемый пищевой контакт Хорошая технологичность Термогерметичность при низкой температуре Оптика Терполимер		
Используется	Двухосно-ориентированная пленка Пленка Пищевая упаковка Упаковка		
Соответствие RoHS	Контактный производитель		
Формы	Гранулы		
Метод обработки	Кокструзия Экструзионная пленка		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность (23°C)	0.895	g/cm ³	ISO 1183
Массовый расход расплава (MFR) (230°C/2.16 kg)	5.0	g/10 min	ISO 1133
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore D, 23°C)	58		ISO 868
Пленки	Номинальное значение	Единица измерения	Метод испытания

Порог теплового уплотнения ¹	90	°C	Internal Method
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Викат Температура размягчения	102	°C	ISO 306/A50
Пиковая температура плавления	131	°C	ASTM D3417

NOTE

1. 1s, 3 bars, 100 mm/min, 100 g/cm

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat