

## Europrene® N OZO 7033/60

Polyvinyl Chloride + NBR

Versalis S.p.A.

### Описание материалов:

Europrene® N OZO 7033/60 is a blend of acrylonitrile-butadiene copolymer and polyvinyl chloride in the ratio 70/30. The fluxing stage is fully achieved during the mechanical mixing thus providing outstanding resistance against ozone and good oil, abrasion and fire resistance together with an excellent processability.

Europrene® N OZO 7033/60 is the low viscosity version of N OZO 7033. It is characterised by an excellent processability in internal and open mixers, high resistance to oils and outstanding fire resistance. This grade exhibits a good compromise between ozone resistance and low temperature performances. Suitable for extrusion and more particularly injection moulding applications, this grade could be vulcanized with sulphur based systems or with peroxides.

Conveyor belts, safety shoe soles, cable jackets, industrial and automotive hoses, fire hoses and all applications where fire and ozone resistance are required together with moderate flexibility at low temperature..

### Главная Информация

Характеристики	Огнестойкий Хорошая стойкость к истиранию Хорошая технологичность Гибкость при низкой температуре Низкая термостойкость Маслостойкий Устойчивость к озону Вулканизируемый
Используется	Автомобильные Приложения Ремни/ремонт ремней Кабельный кожух Детали конвейера Шланг Промышленное применение
Формы	Тюк
Метод обработки	Экструзия Литье под давлением

Физический	Номинальное значение	Единица измерения	Метод испытания
Вязкость Mooney (ML 1+4, 100°C)	60	MU	ASTM D1646
Acrylonitrile Content	23.0	wt%	ASTM D3533
Содержание золы	< 0.5	wt%	ASTM D5667
Летучее вещество	< 1.0	wt%	ASTM D5668

Коэффициент NBR/PVC-Wt/wt

70/30

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat