

Sumiliteresin® PR-53804 I

Phenolic

SBHPP

Описание материалов:

SUMILITERESIN® PR-53804 I is a powder novolac phenolic resin modified CNSL.

Characteristics

SUMILITERESIN® PR-53804 I is a powder novolac phenolic resin that contain about 30% CNSL modified and hexamine about 7%.

For Friction Material : improve flexibility and friction coefficient, also good feeling of braking.

For rubber reinforcing : easy make mixture compound and improve flexibility.

Главная Информация		
Внешний вид	Коричневый	
Формы	Порошок	
Физический	Номинальное значение	Единица измерения
Длина потока (125°C)	3.50 - 5.10	cm
Анализ сита-106µm		%
Тепловой	Номинальное значение	Единица измерения
Температура плавления	75.0 - 88.0	°C
Uncured Properties	Номинальное значение	Единица измерения
Gel Time (165°C)	0.33 - 0.50	min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

