

NHU-PPA N201

Polyphthalamide

Zhejiang NHU Comp. Ltd.

Описание материалов:

NHU-PPA Polymer is a polyamide-class high temperature nylon resin with high distortion temperature, excellent tenacity and frictional resistance. Featuring good melt flow rate, PPA resin boasts excellent injection molding processibility, acid, alkali and general chemical resistance as well as outstanding mechanical strength.

| Главная Информация | | | |
|-------------------------------|------------------------------|--------------------|-----------------|
| Характеристики | Отличная технологичность | | |
| | Высокая прочность | | |
| | Хорошая мобильность | | |
| | Хорошая химическая стойкость | | |
| | Сопротивление щелочи | | |
| | Теплостойкость, высокая | | |
| | Стойкость к кислоте | | |
| Метод обработки | Литье под давлением | | |
| Физический | Номинальное значение | Единица измерения | Метод испытания |
| Номер вязкости | 90.0 | cm ³ /g | ISO 307 |
| Moisture Content ¹ | | % | |
| Содержание золы (750°C) | 0.25 | % | ISO 3451 |
| Тепловой | Номинальное значение | Единица измерения | Метод испытания |
| Температура перехода стекла | 100 | °C | ISO 11357-2 |
| Температура плавления | 323 | °C | ISO 11357-3 |
| NOTE | | | |
| 1. | 150°C, 0.3 hour | | |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

