Escorene™ Ultra UL 04331EL

Ethylene Vinyl Acetate Copolymer Resin

ExxonMobil Chemical

Описание материалов:

UL 04331EL is an HEVA brand, especially designed for photovoltaic cells and packaging applications that require a good balance between viscosity and friction coefficient. It has excellent light transmission performance. The additives contained in UL 04331EL can improve the fluidity and operability of particles.

Главная Информация			
Физический	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Содержание винилацетата	31.4	wt%	ExxonMobil Method
Твердость	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Твердость дюрометра			ASTM D2240
Shaw A, 15 seconds	66		ASTM D2240
Shaw D, 15 seconds	13		ASTM D2240
Механические	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Модуль растяжения	8.00	MPa	ASTM D638
Прочность на растяжение (Break)	6.00	MPa	ASTM D638
Удлинение при растяжении (Break)	900	%	ASTM D638
Тепловой	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Викат Температура размягчения	34.0	°C	ASTM D1525

Юридическое заявление

□□□□□□□□□□□□□,□□□□□□□□□□□□□