

## Elastotite® G 30019T® Hot Melt

Polyurethane

BASF Corporation

### Описание материалов:

ELASTOTITE G 30019T® Hot Melt Polyurethane Reactive Adhesive

Elastotite G 30019T® Hot Melt is a one-component polyurethane reactive hot melt adhesive. The adhesive cures by reacting with ambient moisture to form a strong thermoset polymer. It is designed to give aggressive tack, long open time, and high green strength. It offers clean roll coating without stringing. It is designed for the lamination of various composite components comprising of wood, various plastics and metals.

#### Application:

This adhesive needs to be applied with equipment that will melt and dispense adhesive from 5 gallon pails and 55 gallon drums. Follow your equipment manufacturer procedures for start-up, shut-down and cleanup. If you need to shut down operations for an extended period of time, purge the system with a cleaning solution to prevent adhesive from curing in equipment. Partially used pails or drums can be purged with a dry inert gas and resealed between uses. This adhesive can applied to a substrate using a roll coater or other dispensing equipment such as a heated gun.

#### Recommended Uses:

Recommended for use as a replacement for mechanical fasteners in lamination processes for assembling the bodies of:

Truck/Horse Trailers

Trucks

Buses

Boats

RV

Emergency vehicles

Manufactured Homes

Metal Buildings

### Главная Информация

Используется

Ламинат

Клей

### Дополнительная информация

Appearance: Off White Solid Green Strength: Excellent Application Temperature: 240 to 260°F Open Time: 8 to 10 min Roll Coater Time: 45 min Viscosity @ 250°F: 12000 to 18000 cps Standard Curing Mechanism: Moisture Curing, 72°F & 50% RH

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

### Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

