

Lucofin® 1492M HG

Ethylene Butyl Acrylate Copolymer

Lucobit AG

Описание материалов:

Lucofin® 1492M HG is a chemically modified polyethylene, i.e. EBA grafted with maleic anhydride (MA).

Lucofin® 1492M HG can be used pure or combined with other polymers where improved polarity is required.

Product advantages

easy processing on standard processing equipment

polarity and adhesion to various materials

good compatibility and filler acceptance

good mechanical properties

environmentally sound

Applications

Due to the maleic anhydride content this grade offers excellent adhesion to polar materials and can be used - possibly in combination with Lucofin® 1400HN or Lucofin® 1400MN - to

provide high filler loading, such as ATH (Aluminum tri hydrate) and MDH (Magnesium di hydrate) in HFFR compounds

flexibilize and toughen (impact modification) otherwise brittle plastics (PA, PA/ABS, PBT, PET), including scrap/recycled material

modify melt viscosity and therefore improve processability for PA

compatibilize dissimilar polymer compounds, such as PA/PE and PE/PS

improve bonding and strength in

wood-plastic composite WPC, such as PE, PP/ wood flour

polymer/fiber (glass fiber, natural fiber, long fiber, short fiber) compounds such as PP/long glass fibre

in multilayer films/structures to act as a tie layer between dissimilar materials, such as polyolefins, PE copolymers, ionomers, polyamides, EVOH,

polyesters, polycarbonates and aluminium ,e. g.:

PE / Lucofin® 1492M HG / PA

PE / Lucofin® 1492M HG / PET

PE / Lucofin® 1492M HG / EVOH

Главная Информация

Характеристики	Охрана окружающей среды
	Обрабатываемость, хорошая
	Сплоченность
	Хорошая гибкость
	Хорошая адгезия
Используется	Пластиковая модификация
Формы	Частицы
Метод обработки	Экструзия

Физический	Номинальное значение	Единица измерения	Метод испытания
Плавкий объем-расход (MVR) (190°C/2.16 kg)	7.00	cm³/10min	ISO 1133
Экструзия	Номинальное значение	Единица измерения	
Температура расплава	160 - 270	°C	

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

