

Teflon® FFR 770

Fluoropolymer

DuPont Fluoropolymers

Описание материалов:

DuPont™ Teflon® FFR 770 is fluoropolymer compounded with a nucleating package. The nucleating package in this resin, when combined with nitrogen gas injection, forms uniform foam cells in the insulation. Supplied as white pellets, this resin is used in a gas injected foam extrusion process to produce foamed dielectric insulation.

| Главная Информация | |
|--------------------|-------------------------------|
| Добавка | Нуклеативный агент |
| Характеристики | Foamable |
| | Ядро |
| Используется | Изоляция коаксиального кабеля |
| | Пена |
| | Изоляция |
| Внешний вид | Белый |
| Формы | Гранулы |
| Метод обработки | Экструзия |
| | Экструзия пены |

| Физический | Номинальное значение | Единица измерения | Метод испытания |
|--------------------------------|----------------------|-------------------|-----------------|
| Удельный вес | 2.13 | g/cm ³ | ASTM D792 |
| Массовый расход расплава (MFR) | 30 | g/10 min | ASTM D2116 |

| Тепловой | Номинальное значение | Единица измерения | Метод испытания |
|-------------------------------|----------------------|-------------------|-----------------|
| Пиковая температура плавления | 260 | °C | ASTM D3418 |

| Электрический | Номинальное значение | Метод испытания |
|----------------------------|----------------------|-----------------|
| Диэлектрическая постоянная | | ASTM D2520 |
| 100 kHz | 2.05 | |
| 1 MHz | 2.03 | |
| 600 MHz | 2.00 | |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

