

## ELASTOSIL® R 401/50

Silicone

Wacker Chemie AG

### Описание материалов:

Silicone Rubber, HTV

Spark Plugs Boots, Automotive & Transportation

Vibration Dampers, Automotive & Transportation

Hoses, Automotive, Automotive & Transportation

Protective Clothing, Technical Textiles

Exhaust-Pipe Suspensions, Automotive & Transportation

Molded Seals, Plastics and Rubber Processing

Membranes, Automotive & Transportation

Molded Parts, Automotive, Plastics and Rubber Processing

Molded Parts, Food Contact, Plastics and Rubber Processing

Molded Parts, Technical, Plastics and Rubber Processing

Molded parts; tap water and wastewater contact, Plastics and Rubber Processing

Extrudates, Automotive, Plastics and Rubber Processing

Extrudates, food contact, Plastics and Rubber Processing

Extrudates, Technical, Plastics and Rubber Processing

Extruded parts; tap water and wastewater contact, Plastics and Rubber Processing

Coating of Fabrics and Textiles, Technical Textiles

Sealant Profiles, Construction

### Главная Информация

UL YellowCard	E75704-101818639
Характеристики	Приемлемый пищевой контакт Общее назначение
Используется	Автомобильные Приложения Уплотнение Прокладки Применение питьевой воды Профили Уплотнения Клапаны/Детали Клапана Применение проводов и кабелей
Метод обработки	Каландрирование Прессформа сжатия Экструзия Пресс-форма Экструзионный профиль

Uncured Properties	Номинальное значение	Единица измерения	Метод испытания
Цвет	Clear/Transparent		
Плотность	1.15	g/cm <sup>3</sup>	ISO 1183
Cured Properties	Номинальное значение	Единица измерения	Метод испытания
Твердость по суху (Shore A)	52		DIN 53505
Прочность на растяжение	11.0	MPa	DIN 53504
Удлинение при разрыве	520	%	DIN 53504
Комплект сжатия	34	%	DIN ISO 815-B
Tear Strength	25.0	kN/m	ASTM D624B
Восстановленная устойчивость	53	%	DIN 53512

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

