

Sumiliteresin® PR-2243 I

Phenolic

SBHPP

Описание материалов:

SUMILITERESIN® PR-2243 I is a bis-phenol-A modified novolak phenolic resin. It is generally apply for foundry.

Characteristics

SUMILITERESIN® PR-2243 I is a flake phenolic resin with good properties in foundry manufacture. It is designed in High molecule number and High modified with bis-phenol-A in order to get low thermal expansion, anti peelback and high stick point. It is also improve in bending strength.

SUMILITERESIN® PR-2243 I is preferable add hexamine about 15%/resin when applied in resin coated sand (RCS).

Главная Информация		
Внешний вид	Светло-коричневый	
Формы	Шелковистый	
Физический	Номинальное значение	Единица измерения
Длина потока (125°C)	6.00 - 10.00	cm
Softening Point - B&R;	80 - 95	°C
Uncured Properties	Номинальное значение	Единица измерения
Gel Time (150°C)	1.1 - 1.6	min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

