

## Bayfill® 369 (42.4:100)

Polyurethane (MDI)

Covestro - PUR

### Описание материалов:

Bayfill 369 is a semi-rigid polyurethane foam system designed for automotive interior applications. The Bayfill 369 system is an excellent choice for the production of soft-touch panels, such as instrument panels, door trim, and center consoles. The foam is typically molded in a back-filling process between a soft, exterior skin and a rigid, thermoplastic substrate.

The Bayfill 369 system is supplied as two components. Component A is a polymeric diphenylmethane diisocyanate (PMDI). Component B is a polyol mixture. As with any product, use of the Bayfill 369 system in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

Главная Информация			
Используется	Пена Применение в автомобильной области Автомобильные внутренние детали Оборудование для салона автомобиля Приборная панель автомобиля		
Физический	Номинальное значение	Единица измерения	Метод испытания
Литая плотность	147	kg/m <sup>3</sup>	ASTM D3574A
Отклонение силы сжатия			ASTM D3574C
-- <sup>1</sup>	0.0758	MPa	ASTM D3574C
-- <sup>2</sup>	0.0276	MPa	ASTM D3574C
Комплект сжатия			ASTM D3574D
Cd <sup>3</sup>	62	%	ASTM D3574D
Cd <sup>4</sup>	31	%	ASTM D3574D
Ct <sup>5</sup>	15	%	ASTM D3574D
Ct <sup>6</sup>	31	%	ASTM D3574D
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение			
-- <sup>7</sup>	0.138	MPa	ASTM D3574K
--	0.283	MPa	ASTM D3574E
Удлинение при растяжении			
Fracture <sup>8</sup>	48	%	ASTM D3574K
Fracture	58	%	ASTM D3574E
Эластомеры	Номинальное значение	Единица измерения	Метод испытания
Tear Strength	0.175	kN/m	ASTM D3574F
Термокомплект	Номинальное значение		
Компоненты термокомплекта			

Component a	Mixing ratio by weight: 42
Component B	Mixing ratio by weight: 100

<b>Дополнительная информация</b>	
Part A	
Type: Isocyanate	
Appearance: Dark brown liquid	
Specific Gravity @ 25°C: 1.24	
Viscosity @25°C: 60 cps	
Flash Point PMCC: 149°C	
NCO: 32.2 wt%	
Part B	
Type: Polyol	
Appearance: Colorless to light tan viscous liquid	
Specific Gravity @ 25°C: 1.03	
Viscosity @25°C: 1100 cps	
Flash Point PMCC: 117°C	
Water: 2 wt%	
Hydroxyl Number: 70 KOH/g	
Mold Temperature: 38 to 43°C Demold Time: >90 sec Hand Mix Reactivity at 25°C	
Cream Time: 9 to 17 sec	
Top of Cup Time: 36 to 50 sec	
Gel Time: 39 to 53 to sec	
Rise Time: 67 to 83 sec	
Free-Rise Density: 4.90 to 5.70 lb/ft <sup>3</sup>	
Machine Reactivity at 27 to 32°C	
Cream Time: 6 to 10 sec	
Top of Cup Time: 20 to 22 sec	
Gel Time: 27 to 31 sec	
Rise Time: 44 to 48 sec	
Free-Rise Density: 4.00 to 5.00 lb/ft <sup>3</sup>	
Molded Density: 7 to 10.5 lb/ft <sup>3</sup>	

<b>NOTE</b>	
1.	0.5
2.	After J2 Autoclave
3.	After J2 Autoclave, Cd=compression set as a percentage of the original deflection
4.	50, Cd=compression set as a percentage of the original deflection
5.	50%, Ct=compression set as a percentage of the original thickness
6.	After J2 Autoclave, Ct=compression set as a percentage of the original thickness
7.	Dry Heat Aged at 140°C
8.	Dry Heat Aged at 140°C

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

