

## Honghai CPE 135B

Chlorinated Polyethylene

Weifang Honghai Plastics Technology Co., Ltd.

### Описание материалов:

This product is a kind of saturated thermoplastic elastomer with irregular structure, almost no crystal. It features lower plasticizing temperature and Mooney viscosity, fine processing property, heat resistance, weatherability, oil resistance, flame retardancy, chemical resistance and ozone resistance and so on. It can not only act as impact modifier of hard PVC products to largely produce plastic doors & windows and pipes but also act as special rubber to substitute chloroprene rubber and to produce wires, cables, rubber hose and adhesive tape.

The product is mainly used for special synthetic rubber. In addition, it can act as modifier and solubilizer of general-purposed synthetic rubber. It is widely used in such fields as wires and cables (cables for coal mine and specified wires in standard of UL and VDE etc.), hydraulic rubber hose, rubber hose for vehicles, adhesive tape, adhesive board, PVC profiles, pipe modification, magnetic materials and ABS modification and so on.

Главная Информация	
Характеристики	Обрабатываемость, хорошая Озоновая защита Хорошая химическая стойкость Сопротивление усталости Хорошая устойчивость к погоде Маслостойкость
Используется	Ремешок Применение проводов и кабелей Труба Пластиковая модификация

Физический	Номинальное значение	Единица измерения	Метод испытания
Вязкость Mooney	< 100	MU	ASTM D1646
Содержание хлора	33.0 - 37.0	wt%	GB/T 7139
Decomposition Temperature	> 165	°C	HG/T 2704
Остатки сита-20 меш		%	GB/T 2916
Тепло плавления		J/g	DSC
Испарители		%	GB/T 2914

Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра (Shore A)	< 60		GB/T 2411

Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение	> 6.00	MPa	GB/T 528
Удлинение при растяжении (Break)	> 600	%	GB/T 528

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

