

Tecnoflon® FOR 5361

Fluoroelastomer

Solvay Specialty Polymers

Описание материалов:

TECNOFLON® FOR 5361 is a low viscosity cure incorporated fluoroelastomer terpolymer designed to provide improved low temperature characteristics. Tecnoflon® FOR 5361 exhibits the same excellent heat and chemical resistance expected from Tecnoflon® copolymers.

Some of the basic properties of Tecnoflon® FOR 5361 are:

Improved low temperature performance

Good chemical resistance

Good heat resistance

Very low compression set

Excellent mould release

Lack of mould fouling

Superior mould flow

Tecnoflon® FOR 5361 can be used for injection, compression and transfer molding of O-rings, diaphragms, gaskets, seals, moulded shapes or other items requiring improved low temperature performance.

Tecnoflon® FOR 5361 can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers. This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting.

Finished goods can be produced by a variety of rubber processing methods.

Главная Информация

Характеристики	Хорошая химическая стойкость Хороший поток Хороший выпуск пресс-формы Высокая термостойкость Комплект низкого сжатия Низкая вязкость Терполимер
Используется	Ремни/ремонт ремней Смешивание Диафрагмы Прокладки Шланг Применение при низкой температуре Профили Уплотнения Лист
Внешний вид	Кремowo-белый
Формы	Плита
Метод обработки	Каландрирование

Уплотнение
Прессформа сжатия
Экструзия
Литье под давлением
Литье из смолы

Физический	Номинальное значение	Единица измерения
Вязкость Mooney ¹ (ML 1+10, 121°C)	21	MU
Содержание фтора ²	66	%

NOTE

1. Raw polymer
2. Raw polymer

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

