

## LubriOne™ LB5210-0237 1B NATURAL

Polypropylene

PolyOne Corporation

### Описание материалов:

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.

Главная Информация			
Характеристики	Хорошая износостойкость Смазка		
Соответствие RoHS	Соответствует RoHS		
Внешний вид	Черный		
Формы	Гранулы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.13	g/cm <sup>3</sup>	ASTM D792
Формовочная усадка-Поток	0.10 to 0.30	%	ASTM D955
Механические	Номинальное значение	Единица измерения	Метод испытания
Модуль растяжения <sup>1</sup>	4140	MPa	ASTM D638
Прочность на растяжение <sup>2</sup> (Break)	72.4	MPa	ASTM D638
Флекторный модуль	4840	MPa	ASTM D790
Flexural Strength	110	MPa	ASTM D790
Инъекция	Номинальное значение	Единица измерения	
Температура формы	65.6 to 93.3	°C	
NOTE			
1.	Type I, 5.1 mm/min		
2.	Type I, 5.1 mm/min		

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

### Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

