

SWANCOR Epoxy 905-2

42% стирол

Ероху; Epoxide

SWANCOR IND. CO., LTD.

Описание материалов:

Suitable for flame retardant applications.

Meet ASTM E84 Class 1 while incorporated with 3-5% Antimony Trioxide or 3.75% Nyacol APE 3040.

Excellent mechanical properties and chemical resistance as SWANCOR 901.

Suitable for various fabrication process like hand layup, filament winding, pultrusion etc.

Can comply with US FDA regulation

Главная Информация	
Наполнитель/армирование	Стирол, 42% наполнитель по весу
Характеристики	Кислотоупорный Щелочестойкие Огнестойкий Хорошая химическая стойкость Соленая вода/спрей
Рейтинг агентства	ASTM E 84 FDA неуказанный рейтинг
Формы	Жидкость
Метод обработки	Намотка нити Ручная укладка Пультрузия

Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура отклонения при нагрузке (0.45 MPa, Unannealed)	108	°C	ASTM D648
Термокомплект	Номинальное значение	Единица измерения	Метод испытания
Срок годности (25°C)	26	wk	
Терморегулирующая вязкость (25°C)	380	cP	ASTM D2393

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

