

Dryflex® WS 35M200

Thermoplastic Elastomer

ELASTO

Описание материалов:

With our Dryflex® WS range we have turned the usual water-resistant properties of thermoplastic elastomers (TPE) on their head to create materials that swell up to ten times their volume when immersed in water. These materials have been developed to expand upon contact with aqueous solutions (pH7 to 12) to form a positive seal and prevent the ingress or exit of water.

Material Science

A range of formulations have been developed to offer swell rates from 300 to 1000% when immersed in water. When there is no longer water present the compound shrinks back to its original size, a process of expansion and contraction that can be repeated an unlimited number of times.

The compounds have solid structural integrity; unlike many of the equivalent clay based products which can erode and shatter over time. Compounded in any colour, the water swellable TPE is 100% recyclable and can be processed using conventional fabricating methods, including extrusion and injection moulding. Antimicrobial versions are available.

Applications

Waterstops, building & construction, water treatment plants, tunnels, drains, sewers, tanks, automotive sealant parts, glazing, headlights and cable protection are just a few of the potential applications for Dryflex® WS materials.

We have developed softer grades which offer excellent drapability. They are an ideal choice for water stop applications where the profiles may be coiled or need to be fitted around complex structures.

Главная Информация			
Характеристики	Хорошая химическая стойкость Хорошая устойчивость к погоде Гидрофильная Перерабатываемый материал		
Используется	Автомобильные Приложения Строительные материалы Применение конструкции Остекление Герметики Резервуары		
Формы	Гранулы		
Метод обработки	Литье под давлением		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	1.23	g/cm ³	ISO 2781
Формовочная усадка	1.5	%	
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore A)	35		ISO 868
Тепловой	Номинальное значение	Единица измерения	
Service Temperature ¹	-50 to 75	°C	
Набухание воды-14 дней (23°C)	200	%	

Иньекция	Номинальное значение	Единица измерения
Задняя температура	100 to 110	°C
Средняя температура	110 to 120	°C
Передняя температура	120 to 130	°C
Температура сопла	130 to 140	°C
Температура формы	15.0 to 40.0	°C

NOTE

1. Unstressed Material

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat