

Encapso® K

Rubber

Smooth-On, Inc

Описание материалов:

Encapso® K is a water clear encapsulation rubber that looks just like water and is ideal for a variety of encapsulation and display applications. How Does Encapso® K Work? - Two clear liquids (Part A and Part B) are mixed together in equal amounts. The mixture is then poured around artificial flower stems or over an object. Mixture turns from liquid to a solid, soft rubber over night. When cured, Encapso® K looks just like water and will last a long time.

Encapso® K Advantages:

Non-hazardous - no dangerous chemicals

Soft, Clear Rubber Lasts a long time

Easy to use - mix two liquids in equal amounts and pour

UV Resistant

Cures without generating any dangerous heat or fumes

Minimal Bubble Entrapment

Cures perfectly clear - looks just like water

Cured rubber can be removed from object

Applications for Encapso® K - This rubber is perfect for encapsulating artificial flower stems for creating lasting floral displays. You can also pour

Encapso® K around just about any inanimate object to encapsulate for display. You can also create a variety of display props and novelty items.

Encapso® K can be used to create water/pond effects for small scale model environments. Fully cured Encapso® K can also be crumbled to look like broken glass, diamonds or ice. Add color to Encapso® K with Silc Pig® or Ignite® liquid color pigments.

| Главная Информация | | | |
|-------------------------------|--|--------------------|-----------------|
| Характеристики | Хорошая устойчивость к ультрафиолетовому излучению Высокая четкость Мягкий | | |
| Внешний вид | Прозрачный/прозрачный | | |
| Формы | Жидкость | | |
| Метод обработки | Инкапсулирование | | |
| Физический | Номинальное значение | Единица измерения | Метод испытания |
| Удельный вес | 0.968 | g/cm ³ | ASTM D1475 |
| Удельный объем | 1.03 | cm ³ /g | ASTM D1475 |
| Mixing Ratio | 1A:1B by volume or weight | | |
| Формовочная усадка-Поток | 0.50 | % | ASTM D2566 |
| Твердость | Номинальное значение | Единица измерения | Метод испытания |
| Твердость дюрометра (Shore A) | 20 | | ASTM D2240 |
| Термокомплект | Номинальное значение | Единица измерения | Метод испытания |
| Срок службы горшка (23°C) | 60 | min | ASTM D2471 |
| Терморегулирующая вязкость | 500 | cP | ASTM D2393 |
| Время демолд (23°C) | 1400 | min | |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

