

Manner Flexible PVC M1290

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

Описание материалов:

The needs and requirements of the injection molding industry are unique. When choosing a material for an application, several considerations come into play from the end-use application, to how a material flows, to secondary operations.

Manner Plastics can recommend a flexible PVC material to meet the demands of your application. We serve several industries with injection molding applications including footwear, electrical/electronics, and various consumer products.

The table below shows some of our most popular compounds, but is not a comprehensive view of the Manner Plastics product portfolio. If you do not see a compound offering the performance your application requires, please contact us. We may already have a custom formulation that meets your needs.

All the compounds listed below are UL recognized under UL 94, QMFZ2, and QMFZ8.

All Manner Plastic compounds are RoHS compliant.

Главная Информация			
UL YellowCard	E107449-218515		
Используется	Потребительские приложения		
	Электрическое/электронное применение		
	Обувь		
Рейтинг агентства	UL 94		
	UL QMFZ2		
	UL QMFZ8		
Соответствие RoHS	Соответствует RoHS		
Формы	Гранулы		
Метод обработки	Литье под давлением		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.38 to 1.42	g/cm ³	ASTM D792
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра			ASTM D2240
Shore A	87 to 93		
Shore A, 15 sec	82 to 88		
Эластомеры	Номинальное значение	Единица измерения	Метод испытания
Tensile Stress (100% Strain, 1.52 mm)	8.96	MPa	ASTM D638
Прочность на растяжение (Yield, 1.52 mm)	14.7	MPa	ASTM D638
Удлинение при растяжении (Break, 1.52 mm)	300	%	ASTM D638
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура ломкости	-19.0	°C	ASTM D746

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

